

LR 2254

Modified liquid Epoxy Resin

LR 2254 is a low viscosity epoxy resin based on bisphenol A and modified with an aliphatic monoglycidyl ether.

Specific key data	Property	Value	Test method
	Appearance	Clear, No Contamination	JCTM 001
	Color APHA	100 max.	ASTM D-1209
	Epoxy Value	4.76 – 5.26 eq./kg	ASTM D-1652
	Weight per epoxide	190 – 210 g/eg.	ASTM D-1652
	Viscosity @ 25°C (77°F)	600 – 900 mPa.s	ISO 12058-1
Typical key data	Density at 25°C	1.11 g/cm ³	ISO 1675
	Flash point	≥ 150°C	ISO 2719

INNOVATIVE
TRADING SOLUTIONS FZ LLC
DRIVEN BY PASSION RUN FOR SUCCESS