

TECHNICAL DATA SHEET

MALEIC ANHYDRIDE

Properties	Specification	Reference
1. Appearance	White briquettes	W-LTQ-85 (reference STM-00473)
2. Purity , wt%	99.5 min	W-LTQ-180 (reference STM-01333)
3. Solidification point℃	52.5 min	W-LTQ-86 (ASTM D-1493-67)
4.Stability toHeat Color APHA(90 min at140℃)	40 max	W-LTQ-90 (ASTM-D-3364)
5. Color, APHA	20 max	W-LTQ-89 (ASTM-D-3366-74)
6. Iron content (ppm)	5 max	W-LTQ-87 (AA)
7. Maleic Acid (%)	0.3max	W-LTQ-180 (reference STM-01333)
8. Ash (%)	0.01 max	W-LTQ-88

