

SL 4280 X 80

Epoxy Resin Solution

SL 4280 X 80 is a semi-solid epoxy resin based on Bisphenol A as solvent cut 80% in Xylene.

Specific key data	Property	Value	Test method
	Appearance	Clear, no contamination	JCTM 003
	Color (Gardner)	3 max	ASTM D-1544
	Epoxy Value	2.86 – 3.57 eq/kg	ASTM D-1652
	Weight per epoxide	280 - 350 g/eq	ASTM D-1652
	Solid Content	79 - 81%	JCTM 0097
	Viscosity at 25°C (77°F)	625 - 1275 mPa.s	ISO 12058-1

Typical key data	Property	Value	Test method
	Density at 25°C	1.10 g/cm ³	ISO 1675
	Flash point, closed cup	29°C	DIN 53213

